# LS 17500

# Primary Li-SOCl<sub>2</sub> cell

## 3.6 V A size bobbin cell high energy density

Saft's LS 17500 cell is ideally suited for long-term applications (typically from 5 to 20+ years), featuring low base currents and periodic pulses.

#### **Benefits**

- High capacity and high energy (1139 Wh/l and 589 Wh/kg).
- High voltage response, stable during most of the lifetime of the application.
- Wide operating temperature range (-60°C / +85°C).
- Low self-discharge, compatible with a long operating life (less than 1% per year of storage, at +20 °C, after 1 year).
- Superior resistance to corrosion.
- Low magnetic signature.

#### Key features

- Bobbin construction.
- Well controlled passivation.
- Hermetic construction with glass-tometal seal.
- Stainless steel container.
- Non-flammable electrolyte.
- RoHS and REACH compliance.
- Manufactured in France, China, UK.

## Designed to meet all major quality, safety and environmental standards.

- Safety: UL 1642, IEC 60086-4.
- IEC 60079-11 part 10.5, (T4 temperature rating at +60 °C).
- Transport: UN 3090 and UN 3091.
- Quality: ISO 9001, Saft World Class continuous evaluation program.

#### Typical applications

- Utility Metering.
- Internet of Things.
- Tracking systems.
- Alarms and security.
- Connected sensors.
- Medical devices.




Electrical characteristics [i]	
Nominal capacity (under 3 mA, +20 °C, 2.0 V cut-off	[iii] 3.6 Ah
Open circuit voltage (at +20 °C)	3.67 V
Nominal voltage (under 0.1 mA, +20 °C)	3.6 V
Nominal energy	12.96 Wh
Pulse capability [iv]	Up to 250 mA
Maximum recommended continuous current	100 mA
Operating conditions	
Operating temperature range [v]	-60 °C / +85 °C (-76 °F / +185 °F)
Storage temperatures (max recommended) [vi]	+30 °C (+86 °F)
Physical characteristics [ii]	
Diameter (max)	17.16 mm (0.67 in)
Height (max)	50.77 mm (0.99 in)
Typical weight	23 g (0.81 oz)
Li metal content	approx. 0.9 g
Termination suffix	
CN, CNR	Radial tabs
2 PF, 2 PF, 3PF RP, 4 PF	Radial pins
CNA	Axial leads
FL	Flying leads
Other configurations upon request	
-	

- [i] Typical values relative to cells stored up to one year at + 30 °C max.
- [ii] Sleeved cell.
- [iii] Dependent upon current drain, temperature, cut-off and cell orientation.
- [iv] Under 250 mA / 0.1 second pulses, drained every 2 minutes at + 20 °C from undischarged cells during 24 h, with 10 µA base current, yield voltage readings above 3.0 V after initial stabilisation. The readings may vary according to the pulse characteristics, the temperature, and the cell's previous history. Fitting the cell with a capacitor may be recommended in severe conditions or for high pulse currents. Consult Saft.
- [v] Operation above ambient temperature may lead to reduced capacity and lower voltage readings. Consult Saft.
- [vi] For more severe conditions, consult Saft.



## LS 17500





#### Storage


■ The storage area should be clean, cool (preferably not exceeding +30 °C), dry and ventilated.

#### Warning

- Fire, explosion and burn hazard.
- Do not recharge, short circuit, crush, disassemble, heat above 100 °C (212°F), incinerate, or expose contents to water.
- Do not solder directly to the cell (use tabbed cell versions instead).







### Saft

26, Quai Charles Pasqua, 92300 Levallois Perret -France Tel.: +33 (0)1 49 93 19 18 Fax: +33 (0)1 49 93 19 69 www.saftbatteries.com

### Saft America, Inc.

313 Crescent Street Valdese, NC 28690—USA Tel.: +1 (828) 874 41 11 Fax: +1 (828) 879 39 81 www.saftbatteries.com Doc No: 31029-2-0821 Edition: August 2021 Information in this document is subject to change without notice and becomes contractual only after written confirmation by Saft. Published by the Communication Department. Photo credit: Saft. Produced by CE Marketing Department.

